

TSR 10

Natural Rubber Comparison Chart

Parameter	Unit	Indonesia (SIR)		Malaysia (SMR)		Thailand (STR)		Vietnam (SVR)
		SIR 10	SIR 10VK	SMR 10	SMR 10CV	STR 10	STR 10CV	SVR 10
Dirt (max)	% wt	0.10	0.10	0.08	0.08	0.08	0.08	0.08
Ash (max)	% wt	0.75	0.75	0.75	0.75	0.60	0.60	0.75
Nitrogen (max)	% wt	0.60	0.60	0.60	0.60	0.60	0.60	0.60
Volatile Matter (max)	% wt	0.80	0.80	0.80	0.80	0.80	0.80	0.80
Po (min)		30	30	30	NA	30	NA	30
PRI Index (min)		60	60	50	50	50	50	50
Mooney Viscosity (ML, 1+4, 100°C)		NA	60 +/- 5*	NA	60 +7, -5*	NA	60 +7, -5*	NA

*Not specification status, but are controlled at the producer end.

These figures are limits, not typical values. Typical values will vary by producer.

Astlett Rubber Inc.
Suite 400, 277 Lakeshore Road East
Oakville, ON L6J 1H9
Telephone: (905) 842-2700
Fax: (905) 842-2701
Website: www.astletterubber.com