

Natural Rubber Comparison Chart

Parameter	Unit	Indonesia (SIR)		Malaysia (SMR)		Thailand (STR)		Vietnam (SVR)
		SIR 20	SIR 20VK	SMR 20	SMR 20CV	STR 20	STR 20CV	SVR 20
Dirt (max)	% wt	0.20	0.20	0.16	0.16	0.16	0.16	0.16
Ash (max)	% wt	1.00	1.00	1.00	1.00	0.80	0.80	1.00
Nitrogen (max)	% wt	0.60	0.60	0.60	0.60	0.60	0.60	0.60
Volatile Matter (max)	% wt	0.80	0.80	0.80	0.80	0.80	0.80	0.80
Po (min)		30	30	30	NA	30	NA	30
PRI Index (min)		50	50	40	40	40	40	40
Mooney Viscosity (ML, 1+4, 100°C)		NA	60 +/- 5*	NA	65 +7, -5*	NA	65 +7, -5*	NA

*Not specification status, but are controlled at the producer end.

These figures are limits, not typical values. Typical values will vary by producer.

Astlett Rubber Inc.
 Suite 400, 277 Lakeshore Road East
 Oakville, ON L6J 1H9
 Telephone: (905) 842-2700
 Fax: (905) 842-2701
 Website: www.astletterubber.com