

Natural Rubber Comparison Chart

		Indonesia (SIR)		Malaysia (SMR)		Thailand (STR)	Vietnam (SVR)	
Parameter	Unit	SIR 3CV50	SIR 3CV60	SMR CV50	SMR CV60	STR 5CV	SVR CV50	SVR CV60
Dirt (max)	% wt	0.03	0.03	0.02	0.02	0.04	0.03	0.03
Ash (max)	% wt	0.50	0.50	0.50	0.50	0.60	0.50	0.50
Nitrogen (max)	% wt	0.60	0.60	0.60	0.60	0.60	0.60	0.60
Volatile Matter (max)	% wt	0.60	0.60	0.80	0.80	0.80	0.80	0.80
Po (min)		30	30	NA	NA	NA	NA	NA
PRI Index (min)		60	60	60	60	60	60	60
Mooney Viscosity* (ML, 1+4, 100°C)		50 +/- 5	60 +/- 5	50 +/- 5	60 +/- 5	60 +7 / -5	50 +/- 5	60 +/- 5

*Note: Mooney Viscosity limits at time of production. Values will drift higher over time.

These figures are limits, not typical values. Typical values will vary by producer.

Astlett Rubber Inc.
 Suite 400, 277 Lakeshore Road East
 Oakville, ON L6J 1H9
 Telephone: (905) 842-2700
 Fax: (905) 842-2701
 Website: www.astletterubber.com