

Natural Rubber Comparison Chart

Parameter	Unit	Indonesia (SIR)		Malaysia (SMR)	Thailand (STR)		Vietnam (SVR)	
		SIR 3L	SIR 3WF	SMR L	STR XL	STR 5L	SVR L	SVR 3L
Dirt (max)	% wt	0.03	0.03	0.02	0.02	0.04	0.02	0.03
Ash (max)	% wt	0.50	0.50	0.50	0.40	0.40	0.50	0.50
Nitrogen (max)	% wt	0.60	0.60	0.60	0.50	0.60	0.60	0.60
Volatile Matter (max)	% wt	0.80	0.80	0.50	0.80	0.80	0.80	0.80
Po (min)		30	30	35	35	35	35	35
PRI Index (min)		75	75	60	60	60	60	60
Colour Lovibond Scale (individual value, max)		6.0	NA	6.0	4.0	6.0	4.0	6.0

These figures are limits, not typical values. Typical values will vary by producer.

Astlett Rubber Inc.
 Suite 400, 277 Lakeshore Road East
 Oakville, ON L6J 1H9
 Telephone: (905) 842-2700
 Fax: (905) 842-2701
 Website: www.astletterubber.com