

# SKN4035 E

## Acrylonitrile Butadiene Rubber

### Description

SKN4035 E is a copolymer of butadiene and acrylonitrile manufactured by cold emulsion polymerization technology.

The product is a low Mooney, high acrylonitrile polymer designed to aid in processing operations such as transfer and compression molding.

### End Use

SKN4035 E is recommended for use in industrial and automotive parts such as oil hose.

### Packing

Available in wooden crates of 450 kg net weight. Bales are wrapped in PE film and four-layer craft bags of about 30 kg each.

### Origin

Country: Russia

### Material Specifications

Property	Unit	Specification
Mooney Viscosity*	ML	30—40
Volatile Matter, max	%	0.8
Acrylo-Nitrile content	%	36—40
Elongation at Break, min	%	425
Tensile Strength, min	Mpa	23.0
Stabilizer		Non Staining

Astlett Rubber Inc.  
Suite 205, 277 Lakeshore Road E  
Oakville, ON  
L6J 1H9  
Telephone: (905) 842-2700  
Fax: (905) 842-2701  
Website: [www.astletterubber.com](http://www.astletterubber.com)

Note: The technical data listed in this publication are typical values. Therefore, there may be a slight difference between the elements of a supplied product and the data.